

Barnes

moulding & casting supplies

BARNES PRODUCTS P/L
SYDNEY HEAD OFFICE
6 Homedale Road
Bankstown NSW 2200
Tel: (02) 9793 7555
Fax: (02) 9793 7091

SILPRESSION™

DENTAL GRADE IMPRESSION PUTTY

RTV SILICONE RUBBER

PRODUCT DESCRIPTION

SILPRESSION is a two-component, addition curing, kneadable impression putty designed for taking dental impressions. It is ideally suited to the manufacture of body moulds for the life casting industry. It is also the product of choice for fast impression moulds where time factors are an issue.

TYPICAL PRODUCT USES

Dental Impressions
Life Casting
Any Fast Turnover Moulding

TYPICAL CATALYSED PROPERTIES

Mixed @ 23°C and 50% RH.

Mix Ratio A:B (by weight):	100:100
Mixed Consistency :	Putty
Potlife Life:	2-6 minutes
Cure/Demould Time:	8-15 minutes

TYPICAL CURED PROPERTIES

Colour:	Ochre
Specific Gravity:	1.44
Hardness (Shore A):	

Minutes	8'	10'	15'
Hardness	30	50	55-65

Shrinkage:	<0.2%
------------	-------